




PRODUCT

Fire Cut P-8000 (FCP-8000), Fire Cut P-8000G (FCP-8000G)

2-1

CHEMICAL STRUCTURE



CHEMICAL NAME

Brominated Polystyrene

PROPERTIES

Appearance	FCP-8000	Off-White Powder
	FCP-8000G	Off-White Granule
Bromine Content	ca. 66-68 %	
Volatiles	≤0.5%	

APPLICATION

PBT, PET, PA6, PA66

PACKAGE

25kg paper bag



PRODUCT

Fire Cut P-8000 (FCP-8000), Fire Cut P-8000G (FCP-8000G)**2-2**

FORMULATION

	PBT	PET	PA66
Base Resin	53	53	52
Glass Fiber	30	30	25
FCP-8000	12	12	18
Antimony Trioxide	5	5	5
Oxygen Index (%)	32.0	30.0	33.0
UL94 (0.8 mm)	V-0	V-0	V-0

TG

